

CLAIMS

What is claimed is:

1. A method for producing a fine, highly crystalline material product, the method comprising fluid energy milling a crystalline material using a milling fluid comprising helium at reduced temperature.
2. A method according to claim 1 wherein the milling fluid consists of helium.
3. A method according to claim 1 wherein the temperature of the milling fluid is between -30°C and -120°C .
4. A method according to claim 3 wherein the temperature of the milling fluid is between -50°C and -70°C .
5. A method according to claim 1 wherein the crystalline material comprises a medicament powder.
6. A method according to claim 5 wherein the crystalline material is triamcinolone acetonide.
7. A method according to claim 1 wherein the product has an amorphous content of less than 5%.
8. A method according to claim 7 wherein the product has an amorphous content of less than 2%.
9. A method according to claim 8 wherein the product has an amorphous content of less than 1%.
10. A method according to claim 1 wherein the product comprises a medicament powder in a form suitable for inhalation.

11. A method according to claim 10 wherein the product has a median particle size of less than 10 microns.

12. A crystalline material containing substantially no amorphous content and having a median particle size of less than 2 microns.

13. A crystalline material according to claim 12 having a median particle size of about 1 micron.

10 (14. A crystalline material according to claim 12 which is triamcinolone acetonide.

15. A crystalline material produced by a method according to claim 1.

15 16. A crystalline material according to claim 15 containing substantially no amorphous content and having a median particle size of less than 2 microns.

09871875 060101
T07090 92872860
Add
X1